



(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
02.03.2005 Bulletin 2005/09

(51) Int Cl.7: **C08K 9/04**

(21) Application number: **00302202.7**

(22) Date of filing: **17.03.2000**

(54) **Nanocomposites formed by onium ion-intercalated clay and rigid anhydride-cured epoxy resins**

Nanokomposite hergestellt durch Onium-Ionen interkalierten Ton und zähe mit Anhydrid gehärtete Epoxidharze

Nanocomposites obtenues par argile intercalé avec l'ion onium et résines époxydes rigides durcis avec l'anhydride

(84) Designated Contracting States:
DE FR GB IT NL

(30) Priority: **19.03.1999 US 272277**

(43) Date of publication of application:
27.09.2000 Bulletin 2000/39

(73) Proprietor: **AMCOL INTERNATIONAL CORPORATION**
Arlington Heights, Illinois 60004 (US)

(72) Inventors:
• **Lan, Tie**
Lake Zurich, Illinois 60047 (US)

• **Westphal, Erin K.**
Oakwood Hills, Illinois 60013 (US)

(74) Representative: **W.P. Thompson & Co.**
Coopers Building
Church Street
Liverpool L1 3AB (GB)

(56) References cited:
WO-A-96/08526 **US-A- 5 760 106**
US-A- 5 801 216

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description**FIELD OF THE INVENTION**

5 [0001] The present invention is directed to epoxy nanocomposite compositions containing onium ion and epoxy resin co-intercalated layered materials and exfoliates thereof, in rigid anhydride-cured epoxy resin matrix polymers. A swella-
 ble layered material, such as a phyllosilicate, e.g., a smectite clay, is first intercalated with an onium ion spacing agent,
 as well known in the art, to expand the interlaminar spacing between adjacent layers of the layered material at least
 10 about 3 Å, preferably at least about 5 Å, to at least about 10 Å, preferably to at least about 15 Å. The ion-exchange of
 the layered material inorganic cations with the onium ion (ammonium, phosphonium, oxonium or sulfonium ion) spacing
 agent molecules enables the conversion of the hydrophilic interior clay platelet surfaces to hydrophobic platelet sur-
 faces, so that an anhydride-curable epoxy resin then can be intercalated between the onium ion-expanded planar
 platelets so that the co-intercalated phyllosilicate can be easily exfoliated in the anhydride-cured epoxy matrix polymer
 to form an anhydride-cured epoxy nanocomposite composition. The intercalated epoxy is not chemically or ionically
 15 bound to the platelet surfaces, but intercalates into the onium ion-intercalated interlayer spaces due to the compatibility
 with the onium ion-intercalated platelet surfaces.

[0002] The preferred minimum molar ratio of the onium ion intercalant to the interlayer inorganic cations to convert
 the platelet surfaces from hydrophilic to hydrophobic is at least about 0.5:1, more preferably at least about 1:1. However,
 the molar ratio of the onium ion molecules to the interlayer exchangeable cations, in the interlayer spaces between
 20 phyllosilicate platelets, can be reduced to a substantially lower level, e.g., in the range of from about 0.2:1 to about
 0.5:1 while achieving sufficient spacing between adjacent phyllosilicate platelets for intercalation of the anhydride-
 curable epoxy resin and subsequent platelet exfoliation. The compositions are useful for sealing electronic components;
 adhesives; potting or encapsulation; electronic insulation; filament winding resin binders, and the like, and have in-
 creased glass transition temperatures.

BACKGROUND OF THE INVENTION AND PRIOR ART

[0003] It is well known that phyllosilicates, such as smectite clays, e.g., sodium montmorillonite and calcium montmo-
 rillonite, can be treated with organic molecules, such as organic ammonium ions, to intercalate the organic molecules
 30 between adjacent, planar silicate layers, for bonding the organic molecules with a polymer, such as an epoxy resin,
 for intercalation of the polymer between the layers, thereby substantially increasing the interlayer (interlaminar) spacing
 between the adjacent silicate layers. The thus-treated, intercalated phyllosilicates, having interlayer spacings of at
 least about 10-20 Å and up to about 300 Å, then can be exfoliated, e.g., the silicate layers are separated, e.g., me-
 chanically, by high shear mixing. The individual silicate layers, when admixed with a matrix polymer, e.g., an epoxy -
 35 see U.S. Patent Nos. 4,889,885; 5,554,670; 5,760,106 and 5,801,216 - have been found to improve one or more
 properties of the polymer, such as mechanical strength and/or high temperature characteristics.

[0004] Exemplary prior art composites, also called "nanocomposites", are disclosed in published PCT disclosure of
 Allied Signal, Inc. WO 93/04118 and U.S. Patent No. 5,385,776, disclosing the admixture of individual platelet particles,
 derived from intercalation of layered silicate materials, with a polymer to form a nanocomposite having one or more
 40 properties of the matrix polymer improved by the addition of the exfoliated intercalate. As disclosed in WO 93/04118
 and U.S. Patent No. 5,554,670, the intercalate is formed (the interlayer spacing between adjacent silicate platelets is
 increased) by adsorption of a silane coupling agent or an onium cation, such as a quaternary ammonium compound,
 having a reactive group which is compatible with the matrix polymer. Such quaternary ammonium cations are well
 known to convert a highly hydrophilic clay, such as sodium montmorillonite or calcium montmorillonite, into an organ-
 45 ophilic clay capable of sorbing organic molecules.

[0005] US 5801,216 describes a resin clay composite comprising:

- (a) a cured epoxy resin which has been cured by a curing agent; and
- (b) a smectite clay having layers with the cured epoxy resin and with organic onium cations separating the layers,
 50 wherein the onium cations are protonated unsubstituted alkyl ammonium cations containing 3 to 22 carbon atoms
 in the alkyl ammonium cations, wherein the composition contains between about 5 and 50 weight percent of the
 clay and wherein the average separation between the clay layers in the composition is between 7 Å to 300 Å , and
 wherein the curing agent is non-interfering with the onium cations in achieving separation of the layers of the
 smectite clay.

55 [0006] US 5,760 describes a method for providing a flexible sealant in an apparatus the improvement which com-
 prises:

providing as the sealant a resin-clay composite composition which comprises:

- (a) a cured epoxy resin; and
- (b) a smectite clay having layers with the cured epoxy resin separating the layers, the galleries containing the cured epoxy resin and organic onium cations wherein the onium cations are protonated unsubstituted alkyl ammonium cations containing 3 to 22 carbon atoms in the alkyl ammonium cations. Wherein the composition contains between about 5 and 50 weight percent of the clay, and wherein the average separation between the clay layers corresponds to a gallery height of 7 Å to 33 Å.

[0007] Both of these specifications are limited to the use of protonate onium ions.

[0008] In accordance with the present invention, intercalates are prepared by contacting a phyllosilicate with an onium ion that does not contain an epoxy-reactive functional moiety so that a subsequently intercalated anhydride-cured epoxy does not bond to the intercalated onium ion molecule.

[0009] In accordance with an important feature of the present invention, best results are achieved by mixing the layered material with the onium ion molecules in a molar ratio of at least about 0.5:1 onium ions to layered material interlayer exchangeable cations, preferably at least about a 1:1 molar ratio of onium ions to exchangeable platelet cations. Regardless of the concentration of onium ion spacing/coupling agent, the intercalating composition should have an onium ion layered material weight ratio of at least 1:20, preferably at least 1:10, more preferably at least 1:5, and most preferably at least about 1:4 to achieve sufficient ion-exchange of the protonated atom of the onium ion molecule (N⁺, P⁺, O⁺ or S⁺) with inner surface cations of the platelets of the layered material to achieve efficient intercalation and bonding of the onium ion compound at the platelet surfaces for subsequent exfoliation, particularly after epoxy resin intercalation. The onium ion intercalant compound sorbed between and bonded to (ion-exchanged with) the silicate platelets causes sufficient separation or added spacing between adjacent silicate platelets for easy co-intercalation of the anhydride-curable epoxy resin. It should be understood that when determining the molar ratio of onium ions to layered material, it is the moles of onium ion (without the dissociated anion) that is calculated, without considering the molecular weight of the dissociated anion once the onium ion compound is solubilized.

[0010] One prior art method of preparing layered silicate-epoxy nanocomposites is disclosed by Giannelis in U.S. Patent No. 5,554,670. In accordance with the method disclosed in the Giannelis '670 patent, a smectite-type clay is first contacted with an organic compound containing alkylammonium ions having functional groups which are reactive to epoxy resin molecules. The clay layers are attached to the polymer network via onium ion-exchange with the clay platelet cations - the epoxy resin reacting with the reactive functionality on the onium ion molecule. The nanocomposites disclosed in the '670 patent exhibit a slightly increased glass transition temperature - the dynamic storage modulus of the nanocomposite was considerably higher in the glassy region and very much higher in the rubbery region when compared with the pristine matrix polymer.

[0011] It has now been found that the glass transition temperature (T_g) of rigid anhydride-cured epoxy resins (rigid being defined herein as having a T_g > 30°C) can be unexpectedly raised by mixing the anhydride-curable epoxy resin with a nanomer formed by intercalating a layered silicate material, such as a phyllosilicate, with organic onium ions to space the adjacent platelets sufficiently for intercalation of an anhydride-curable epoxy resin, and mixing the onium ion-intercalated layered material with an anhydride-curable epoxy resin and an anhydride curing agent to co-intercalate the anhydride-curable epoxy resin with onium ions and the anhydride curing agent to form the nanocomposite composition.

[0012] In principle, the anhydride-curable epoxy resin and onium ion co-intercalants of the present invention perform together in the gallery of the layered materials to make the inorganic layered materials compatible with the epoxy matrix polymer and form the nanocomposite. The anhydride-cured epoxy resin does not bond to the onium ions or to the phyllosilicate platelets since the onium ions are not epoxy-reactive functionalized. The co-intercalates made by the process of the present invention can be admixed with all market available epoxy resin systems to form nanocomposites. Examples of suitable epoxy resins include: Bisphenol A-derived resins, Epoxy cresol Novolac resins, Epoxy phenol Novolac resins, and the like.

DEFINITIONS

[0013] Whenever used in this Specification, the terms set forth shall have the following meanings:

[0014] "Layered Material" shall mean an inorganic material, such as a smectite clay mineral, that is in the form of a plurality of adjacent, bound layers and has a thickness, for each layer, of about 3 Å to about 50 Å, preferably about 10 Å.

[0015] "Platelets" shall mean individual layers of the Layered Material.

[0016] "Intercalate" or "Intercalated" shall mean a Layered Material that includes organic quaternary onium ion molecules disposed between and bound to adjacent platelets of the Layered Material that are ion-exchanged for layered material exchangeable cations to increase the interlayer spacing between the adjacent platelets at least 3 Å, preferably

at least 5 Å to an interlayer spacing of, for example, at least about 10 Å, preferably to at least about 15 Å, and the layered material also includes epoxy molecules disposed between adjacent layered material platelets until the platelets have a d-spacing of at least about 20 Å, preferably about 20-35 Å. The epoxy is bound neither to the layered material platelets nor to the onium ions.

[0017] "Intercalation" shall mean a process for forming an Intercalate.

[0018] "Organic Onium Ions" shall mean a monomeric organic cation that includes a N⁺, P⁺, O⁺ or S⁺ cation which is capable of ion-exchanging with inorganic cations, such as Li⁺, Na⁺, K⁺, Ca²⁺, and Mg²⁺ in the interlayer space between Layered Material Platelets. The quaternary onium ions are sorbed between Platelets of the Layered Material and ion-exchanged at protonated N⁺, P⁺, O⁺ or S⁺ ions with at least the Na⁺ cations on the platelet surfaces to form an Intercalate.

[0019] "Epoxy resin" shall mean an epoxy polymer, or a monomer or prepolymer (oligomer) that can react with one or more anhydride curing agents to yield network thermosetting epoxy polymers. The polymer, monomer or prepolymer (oligomer) shall have at least one three-membered cyclic ether group commonly referred to as an epoxy group, 1,2-epoxide or oxirane.

[0020] "Co-intercalation" shall mean a process for forming an intercalate by intercalation of quaternary onium ions and an anhydride-curable epoxy resin and, optionally, an anhydride curing agent for the anhydride-curable epoxy resin.

[0021] "Concentrate" shall mean an intercalate comprising a layered silicate inorganic material including ion-exchanged and intercalated quaternary onium ions and an intercalated anhydride-curable epoxy resin, said intercalate combined with an anhydride-curable epoxy matrix polymer, in an intercalate concentration greater than needed to improve one or more properties of the matrix polymer, so that the concentrate can be mixed with additional matrix polymer to form a nanocomposite composition or a commercial article, and an anhydride curing agent added to the concentrate or to the nanocomposite composition.

[0022] "Intercalating Carrier" shall mean a carrier comprising water with or without an organic solvent used together with the quaternary onium ions and/or with the anhydride-curable epoxy resin to form an Intercalating Composition capable of achieving quaternary onium ion Intercalation of the Layered Material and, at the same time or separately, Intercalation of the co-intercalant anhydride-curable epoxy resin, and optionally an anhydride curing agent for the epoxy, between platelets of the Layered Material.

[0023] "Intercalating Composition" or "Intercalant Composition" shall mean a composition comprising quaternary onium ions and/or an Intercalant anhydride-curable epoxy resin, an Intercalating Carrier for the quaternary onium ions and/or for the anhydride-curable epoxy resin, a Layered Material, and optionally an anhydride curing agent for the epoxy.

[0024] "Exfoliate" or "Exfoliated" shall mean individual platelets of an Intercalated Layered Material, or tactoids or clusters of individual platelets, e.g., 2-10 platelets, preferably 2-5 platelets, that are smaller in total thickness than the non-exfoliated Layered Material, capable of being dispersed as individual platelets and/or tactoids throughout an anhydride-cured epoxy resin.

[0025] "Exfoliation" shall mean a process for forming an Exfoliate from an Intercalate.

[0026] "Matrix Polymer" shall mean an anhydride-curable epoxy resin that the Intercalate and/or Exfoliate is dispersed throughout.

SUMMARY OF THE INVENTION

[0027] In brief, the present invention is directed to nanocomposite composition prepared by co-intercalation of quaternary onium ions and an anhydride-curable epoxy resin between the planar layers of a swellable layered silicate material, such as a phyllosilicate, preferably a smectite clay. The spacing of adjacent layers of the layered materials is expanded at least 3 Å, preferably at least about 5 Å, to at least about 10 Å, preferably to at least about 15 Å usually to about 15 Å to about 30 Å, e.g., 18 Å, by quaternary onium ion intercalation and ion-exchange with interlayer cations, such as Li⁺, Na⁺, K⁺, Ca²⁺, Mg²⁺ or other inorganic cations that are naturally disposed in the interlayer space between adjacent platelets or layers of the swellable layered silicate materials. The ion-exchange binding between the quaternary onium ions and the platelet surface, via ion-exchange with intergallery inorganic cations, eliminates the presence of water molecules associated with the inorganic cations. Therefore, the quaternary onium ion-exchange enables the conversion of the hydrophilic interior clay surface to hydrophobic and, therefore, hydrophobic epoxy polymer molecules can then be intercalated into the clay galleries to increase the d-spacing of adjacent layers to at least about 20 Å, preferably about 25-35 Å.

[0028] Accordingly, one aspect of the present invention is to provide epoxy nanocomposite compositions, methods of manufacturing the nanocomposite compositions, epoxy-intercalated nanomers, and methods of manufacturing the nanomers for improving thermal, mechanical and/or gas-impermeability characteristics of anhydride-cured epoxy resins.

[0029] Another aspect of the present invention is to provide intercalates, and methods of manufacturing the interca-

lates, formed by intercalating a quaternary onium ion spacing/coupling agent that is not reactive with an anhydride-curable epoxy resin into a layered material, such as a smectite clay, and simultaneously or subsequently co-intercalating an anhydride-curable epoxy resin, said co-intercalated layered material capable of substantially increasing the thermal, mechanical, and/or gas-impermeability characteristics of an anhydride-curable rigid epoxy resin when added thereto

[0030] The above and other aspects and advantages of the present invention will become more apparent from the following detailed description of the preferred embodiments, read in conjunction with the drawings.

BRIEF DESCRIPTION OF THE DRAWINGS


[0031]

FIG. 1 is a graph showing the thermal analysis of a DER331 epoxy resin, ECA100 anhydride curing agent with and without a curing accelerator compound (AP-6E) with and without 10 parts of clay intercalate (per hundred parts (phr) of epoxy) - intercalated with the same epoxy resin and the same anhydride curing agent, added to the same anhydride-cured epoxy matrix polymer, showing a substantial increase in modulus with the intercalate; and FIG. 2 is a graph showing the dynamic mechanical analysis (DMA) for DER331 epoxy resins with a ECA 100 curing agent and a AP-6E curing accelerator with 20% by weight of an octadecyltrimethyl ammonium chloride-intercalated sodium montmorillonite clay, based on the weight of the epoxy.

[0032] On both figures the curves identified as Sm are for storage modulus and refer to the left hand vertical axis and the curve identified as Td are for tan-delta and refer to the right hand axis.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0033] Suitable onium ion molecules are not epoxy reactive and are quaternary onium ions. The quaternary onium ions have the general structure:



wherein X=N, P, O or S and R₁, R₂, R₃ and R₄, same or different, are epoxy non-reactive organic radicals and can be aliphatic, aralkyl or aromatic, linear or branched.


[0034] The present invention is directed to a method of preparing intercalated layered materials prepared by co-intercalation of quaternary onium ions and anhydride-curable epoxy resins between the planar layers of a swellable layered material, such as a phyllosilicate, preferably a smectite clay. With the assistance of the intercalating carrier, the quaternary onium ions and the anhydride-curable epoxy polymer molecules will co-intercalate into the galleries of the layered materials to form intercalates or intercalate concentrate compositions capable of easy exfoliation.

[0035] While the invention described herein is disclosed by way of the preferred embodiment via expanding the interlaminar spacing between adjacent platelets of a layered silicate material, e.g., a phyllosilicate, by first intercalating quaternary onium ions between the silicate platelets, prior to or simultaneously with intercalating an anhydride-curable epoxy resin intercalant, it should be understood that the anhydride-curable epoxy resin intercalant can be intercalated between and complexed to the internal platelet faces by other well known mechanisms, such as the dipole/dipole (direct intercalation of the anhydride-curable epoxy resin oligomer or polymer) method disclosed in this Assignee's U.S. Patent Nos. 5,880,197 and 5,877,248, hereby incorporated by reference; and by the acidification technique, by substitution with hydrogen (ion-exchanging the interlayer cations with hydrogen by use of an acid or ion-exchange resin) as disclosed in the Deguchi U.S. Patent No. 5,102,948, and in the Pinnavaia, et al. U.S. Patent No. 5,853,886, hereby incorporated by reference.


[0036] The present invention also is directed to the exfoliate and nanocomposite compositions which are prepared from the intercalate or intercalate concentrate compositions. The exfoliate can be prepared by diluting the concentrate in more anhydride-curable epoxy polymer, or adding the epoxy polymer, e.g., polymerized epoxy resins, and then

curing with one or more anhydride curing agents.

[0037] In general, suitable epoxy and phenoxy resins are aliphatic-, cycloaliphatic-, or aromatic-based epoxy resins, such as, for example, epoxy resins represented by structural formulae I and II:




(I)



(II)


, wherein each A is, independently, a divalent hydrocarbyl group having 1 to about 12, preferably 1 to about 6, and most preferably 1 to about 4, carbon atoms; each R is, independently, hydrogen or an alkyl group having 1 to about 3 carbon atoms; each X is, independently, hydrogen, a hydrocarbyl or hydrocarbyloxy group having 1 to about 12, preferably 1 to about 6, and most preferably 1 to about 4, carbon atoms, or a halogen atom, preferably chlorine or bromine; n is 0 or 1, and n' has an average value of about 2 to about 30, and preferably 10 to about 30.

[0038] In particular, the preferred epoxy and phenoxy resins are the (diglycidyl ether/bisphenol-A) resins, i.e., polyether diepoxides prepared by the polymeric addition of bisphenol-A (III)




(III)

and the diglycidyl ether of bisphenol-A (IV).



(IV)


In this case, the epoxy resin is a mixture including polymeric species corresponding to different values of n' in the following idealized formula V:




(V)

wherein n' is a number from about 2 to about 30.


[0039] In addition to bisphenol-A, useful epoxy and phenoxy resins can be prepared by advancing a diglycidyl ether of a bisphenol listed below with an exemplary, but nonlimiting, bisphenol listed below:



5




10




15

20




25

30




35

40















45








50






55












25 **[0040]** Other anhydride-curable epoxy resins that can be used as the co-intercalants of the present invention are prepared from the following starting epoxy-containing materials. These epoxy-containing materials are reacted with bisphenol-A or another bisphenol to adjust the molecular weight of the epoxy resin, as desired.




[0041] Other suitable epoxy resins useful in accordance with the present invention include epoxy novolac resins.

[0042] Epoxy novolac resins useful in making the nanocomposite composition of the present composition include polyfunctional epoxy resins having an epoxy functionality of about 2, and preferably greater than about 2, to about 6, and preferably greater than about 2 to about 5. The epoxy novolac resins include low molecular weight resins having an epoxide equivalent weight (EEW) of about 100 to about 220, and preferably an EEW of about 150 to about 210.

[0043] Epoxy novolac resins useful in the present invention include for example, but are not limited to, epoxy phenol


novolac resins. Epoxy phenol novolac resins are represented by general structural formula (VI) wherein n is about 0.2 to about 4.



The multifunctional epoxy phenol novolac resins contain a phenolic hydroxyl group per phenyl ring in random para-para', ortho-para', and ortho-ortho' combinations. Epoxidation with epichlorohydrin yields the highly functional epoxy phenol novolac resins. The epoxy phenol novolac resin can be a high viscosity liquid (i.e., n about 0.2) or a solid (i.e., n greater than 3).


[0044] Nonlimiting examples of epoxy phenol novolac resins useful in the present invention are ARALDITE® EPN 1139 available from CIBA-GEIGY Corp., Hawthorne, NY, and D.E.N. 431, available from Dow Chemical Co., Midland, MI. These epoxy phenol novolac resins have an n value (from structural formula I) of 0.2, an EEW of 175 and an epoxy functionality of 2.2. Other nonlimiting examples of epoxy phenol novolac resins are D.E.N. 438 and ARALDITE® EPN 1138, available from Dow Chemical Co. and CIBA-GEIGY Corp., respectively, and having an n value of 1.6, an EEW of 178 and an epoxy functionality of 3.6; and D.E.N. 439 available from Dow Chemical Co. and having an n value of 1.8, an EEW of 200 and an epoxy functionality of 3.8.

[0045] Another useful class of epoxy novolac resins is the epoxy cresol novolac resins depicted in general structural formula (VII), wherein n is about 1.7 to about 4.4.




The epoxy cresol novolac resins are prepared by glycidylation of o-cresolformaldehyde condensates in the same manner as the epoxy phenol novolac resins. The epoxy functionality of the epoxy cresol novolac resins is about 2.7 to about 5.4.

[0046] Other useful epoxy novolac resins, i.e., polyfunctional epoxy resins, include but are not limited to a polynuclear phenol-glycidyl ether resin, such as the tetraglycidyl ether of tetrakis(4-hydroxyphenyl)ethane depicted in structural formula (VIII), and having an EEW of about 185 to about 210 and a theoretical epoxy functionality of four.



(VIII)


[0047] A tetraglycidylmethylenedianiline resin exemplified in structural formula (IX), as N,N,N',N'-tetraglycidyl-4,4'-diaminophenylmethane, having an EEW of about 117 to about 133 and an epoxy functionality of about 4 also can be used as the epoxy novolac resin.



(IX)

In addition, triglycidyl p-aminophenol resins, available from CIBA-GEIGY Corp., and having an EEW of about 105 to about 114 and an epoxy functionality of about 3 can be used as the epoxy novolac resin.

[0048] Another exemplary epoxy novolac resin is a triglycidyl isocyanurate depicted in structural formula (X) and having an epoxy functionality of about 3 and an EEW of about 108.



(X)

[0049] An epoxy novolac resin provides a sufficient number of crosslinking sites such that the resulting anhydride-cured epoxy nanocomposite composition is rigid and has an unexpectedly high Tg.

[0050] Any anhydride curing agent can be used to cure the above-described epoxy resins. Some of the available anhydride curing agents for epoxies, together with their suggested cure schedule, are listed in Table I:

TABLE I

CURING AGENT	SUGGESTED CURE SCHEDULE
Nadic methyl anhydride (NMA)	2 hours at 90°C ⁺ 4 hours at 165°C ⁺ 16 hours at 200°C ⁺
Hexahydrophthalic anhydride (HHPA)	2 hours at 100°C ⁺ 2-6 hours at 150°C ⁺
Trimellitic anhydride (TMA)	24 hours at 150-180°C ⁺
Dodecenyl succinic anhydride (DDSA)	2 hours at 100°C ⁺ 4-6 hours at 150°C ⁺
Phthalic anhydride (PA)	24 hours at 120°C ⁺ 8 hours at 150°C ⁺
Methyl hexahydrophthalic anhydride (MHHPA)	3 hours at 100°C ⁺ 6 hours at 140°C ⁺
Tetrahydrophthalic anhydride (THPA)	24 hours at 120°C ⁺ 8 hours at 150°C ⁺
Methyl tetrahydrophthalic anhydride (MTHPA)	2 hours at 90°C ⁺ 4 hours at 150°C ⁺

[0051] Sorption of the quaternary onium ions should be sufficient to achieve expansion of the interlayer spacing of adjacent platelets of the layered material (when measured dry) to at least about 10 Å, preferably to at least about 15 Å, more preferably to at least about 20 Å, and after intercalation of the anhydride-curable epoxy resin, and optionally an anhydride curing agent for the epoxy, the interlayer spacing preferably is in the range of about 25-45 Å. To achieve intercalates that can be exfoliated easily, the molar ratio of quaternary onium ions to interlayer cations should be at least 0.5:1, preferably about 1:1 or more. The co-intercalation of the quaternary onium ions and anhydride-curable epoxy intercalants into the clay interlayer spacing can be achieved by intercalation of the anhydride-curable epoxy intercalant after intercalation of the quaternary onium ions; or by simultaneous intercalation of quaternary onium ions and anhydride-curable epoxy, and optionally an anhydride curing agent for the epoxy, at ambient or elevated temperatures.

[0052] Once exfoliated, the platelets of the intercalate are predominantly completely separated into individual platelets and the originally adjacent platelets no longer are retained in a parallel, spaced disposition, but are free to move as predominantly individual platelets throughout an anhydride-cured epoxy matrix polymer melt for enhancing one or more properties, particularly strength and glass transition temperature, of the matrix, anhydride-cured epoxy polymer. The predominantly individual phyllosilicate platelets, having their platelet surfaces ion-exchanged with the quaternary onium ion molecules, are randomly, homogeneously and uniformly dispersed, predominantly as individual platelets, throughout the anhydride-cured epoxy polymer to achieve new and unexpected strength and glass transition temperatures in a rigid epoxy nanocomposite composition.

[0053] Any swellable layered material that sufficiently sorbs the onium ion intercalant to increase the interlayer spacing between adjacent phyllosilicate platelets to at least about 10 Å (when the phyllosilicate is measured dry) may be used in the practice of this invention. Useful swellable layered materials include phyllosilicates, such as smectite clay minerals, e.g., montmorillonite, particularly sodium montmorillonite; magnesium montmorillonite and/or calcium montmorillonite; nontronite; beidellite; volkonskoite; hectorite; saponite; sauconite; sobockite; stevensite; svinfordite; vermiculite; and the like. Other useful layered materials include micaceous minerals, such as illite and mixed layered illite/smectite minerals, such as rectorite, tarosovite, ledikite and admixtures of illites with the clay minerals named above.

[0054] Other layered materials having little or no charge on the layers may be useful in this invention provided they can be intercalated with the quaternary onium ion intercalant to expand their interlayer spacing to at least about 10 Å. Preferred swellable layered materials are phyllosilicates of the 2:1 type having a negative charge on the layers ranging from about 0.15 to about 0.9 charges per formula unit and a commensurate number of exchangeable metal cations in

the interlayer spaces. Most preferred layered materials are smectite clay minerals such as montmorillonite, nontronite, beidellite, volkonskoite, hectorite, saponite, sauconite, sobockite, stevensite, and svinfordite.

[0055] As used herein the "interlayer spacing" refers to the distance between the internal faces of the adjacent layers as they are assembled in the layered material before any delamination (exfoliation) takes place. The interlayer spacing is measured when the layered material is "air dry", e.g., contains about 3-6% by weight water, e.g., 5% by weight water based on the dry weight of the layered material. The preferred clay materials generally include interlayer cations such as Na^+ , Ca^{+2} , K^+ , Mg^{+2} , NH_4^+ and the like, including mixtures thereof.

[0056] Some intercalates require a shear rate that is greater than about 10 sec^{-1} for such relatively thorough exfoliation. Other intercalates exfoliate naturally or by heating, or by applying low pressure, e.g., 0.5 to 60 atmospheres above ambient, with or without heating. The upper limit for the shear rate is not critical. In the particularly preferred embodiments of the invention, when shear is employed for exfoliation, the shear rate is from greater than about 10 sec^{-1} to about $20,000 \text{ sec}^{-1}$, and in the more preferred embodiments of the invention the shear rate is from about 100 sec^{-1} to about $10,000 \text{ sec}^{-1}$.

[0057] When shear is employed for exfoliation, any method which can be used to apply a shear to the intercalant/carrier composition can be used. The shearing action can be provided by any appropriate method, as for example by mechanical means, by thermal shock, by pressure alteration, or by ultrasonics, all known in the art. In particularly useful procedures, the composition is sheared by mechanical methods in which the intercalate, with or without the carrier or solvent, is sheared by use of mechanical means, such as stirrers, Banbury® type mixers, Brabender® type mixers, long continuous mixers, and extruders. Another procedure employs thermal shock in which shearing is achieved by alternatively raising or lowering the temperature of the composition causing thermal expansions and resulting in internal stresses which cause the shear. In still other procedures, shear is achieved by sudden pressure changes in pressure alteration methods; by ultrasonic techniques in which cavitation or resonant vibrations which cause portions of the composition to vibrate or to be excited at different phases and thus subjected to shear. These methods of shearing are merely representative of useful methods, and any method known in the art for shearing intercalates may be used.

[0058] Mechanical shearing methods may be employed such as by extrusion, injection molding machines, Banbury® type mixers, Brabender® type mixers and the like. Shearing also can be achieved by introducing the layered material and intercalant monomer at one end of an extruder (single or double screw) and receiving the sheared material at the other end of the extruder. The temperature of the layered material/intercalant monomer composition, the length of the extruder, residence time of the composition in the extruder and the design of the extruder (single screw, twin screw, number of flights per unit length, channel depth, flight clearance, mixing zone, etc.) are several variables which control the amount of shear to be applied for exfoliation.

[0059] To achieve the full advantage of the present invention, exfoliation should be sufficiently thorough to provide at least about 80% by weight, preferably at least about 85% by weight, more preferably at least about 90% by weight, and most preferably at least about 95% by weight delamination of the layers, and after exfoliation, some tactoids that include 2-10, particularly 2-5 platelets or, more preferably, individual platelet particles that can be substantially homogeneously dispersed in the anhydride-curable epoxy matrix polymer. As formed by this process, the platelet particles or platelet multilayer tactoids dispersed in the matrix anhydride-curable epoxy resin have the thickness of the individual layers, or small multiples less than about 10, preferably less than about 5 and more preferably less than about 3 of the layers, and still more preferably 1 or 2 layers. In the preferred embodiments of this invention, intercalation and delamination of every interlayer space is complete so that all or substantially all individual layers delaminate one from the other to form separate platelet particles for admixture with the carrier or solvent. The compositions can include the layered material as all intercalate, completely without exfoliation, and later, after compounding with the matrix polymer, such as by extrusion with a melt of the matrix polymer, exfoliation is achieved.

[0060] Epoxy molding compositions comprising an anhydride-cured epoxy polymer containing a desired loading of platelets and tactoids obtained from exfoliation of the intercalates manufactured according to the invention are outstandingly suitable for the production of sheets and panels having valuable properties. Such sheets and panels may be shaped by conventional processes such as vacuum processing or by hot pressing to form useful objects. The sheets and panels according to the invention are also suitable as coating materials for other materials comprising, for example, wood, glass, ceramic, metal or other plastics, and outstanding strengths can be achieved using conventional adhesion promoters, for example, those based on vinyl resins. The sheets and panels can also be laminated with other plastic films and this is preferably effected by co-extrusion, the sheets being bonded in the molten state. The surfaces of the sheets and panels, including those in the embossed form, can be improved or finished by conventional methods, for example by lacquering or by the application of protective films.

[0061] Matrix polymer/platelet composite materials are especially useful for fabrication of extruded films and film laminates, as for example, films for use in food packaging. Such films can be fabricated using conventional film extrusion techniques. The films are preferably from about 10 to about 100 microns, more preferably from about 20 to about 100 microns and most preferably from about 25 to about 75 microns in thickness.

[0062] The homogeneously distributed platelet particles, exfoliated in accordance with the present invention, and

matrix anhydride-cured epoxy polymer that form the nanocomposites of one embodiment of the present invention are formed into a film by suitable film-forming methods. Typically, the composition is melted and forced through a film forming die. The film of the nanocomposite may go through steps to cause the platelets to be further oriented so the major planes through the platelets are substantially parallel to the major plane through the film. A method to do this is to biaxially stretch the film. For example, the film is stretched in the axial or machine direction by tension rollers pulling the film as it is extruded from the die. The film is simultaneously stretched in the transverse direction by clamping the edges of the film and drawing them apart. Alternatively, the film is stretched in the transverse direction by using a tubular film die and blowing the film up as it passes from the tubular film die. The films may exhibit one or more of the following benefits: increased modulus; increased wet strength; increased dimensional stability; decreased moisture adsorption; decreased permeability to gases such as oxygen and liquids, such as water, alcohols and other solvents.

[0063] The onium ion-intercalated treated montmorillonite clays can be incorporated into the epoxy resin, or epoxy-anhydride mixture, and the quaternary onium ion-intercalated montmorillonite clay functions as an accelerator for the epoxy-anhydride curing reaction, without the need for a curing accelerator.

[0064] The quaternary onium ion-intercalated layered material, i.e., montmorillonite clay, can be added to the epoxy resin from room temperature up to about 120°C. The weight percentage or parts per hundred (phr) of intercalated clay added to the matrix polymer can be in the range of 1 to 50, with a preferred range of 5 to 35 phr, based on the total weight of the nanocomposite composition. The elevated temperature will reduce the viscosity of the epoxy resin and facilitate the dispersion of the onium ion-intercalated layered material, i.e., clay. The anhydride curing agent and optional accelerator can be added to the premixed epoxy-clay mixture in the form of the intercalate and/or to the intercalate/matrix polymer (nanocomposite) composition. The whole composition can be degassed and cured under normal curing cycles.

[0065] In the above-mentioned incorporation routes of the treated clays into the epoxy-anhydride composition, there is no need to add a curing accelerator to the epoxy resin-clay mixture. The resin will be cured without the addition of accelerator in the presence of the onium ion-intercalated layered material. The accelerator-free nanocomposites demonstrate comparable increased modulus and glass transition temperatures compared with the nanocomposites with accelerators.

[0066] The layered material, i.e., montmorillonite clay, is intercalated with non-functionalised quaternary onium ions, e.g., quaternary ammonium ions, such as octadecyl trimethyl ammonium (C183M), octadecyl dimethyl benzyl ammonium (C182MB), octadecyl methyl bis-hydroxyethyl ammonium chloride (Q182, 50% solution), and/or di-tallow dimethyl ammonium (DTDm). The montmorillonite clay is intercalated and exchanged by ion-exchange reaction with the quaternary onium ion intercalant at molar ratios of the quaternary onium ion to the clay cation exchange capacity of preferably 0.5-1:1. The quaternary onium ion-intercalated montmorillonite clays preferably are then reduced by known particle size reduction methods, such as hammer mill, jet mill, or air-classifier mill. The onium ion-intercalated layered material can be mixed with the anhydride-curable epoxy resin first, then the anhydride curing agent and accelerator (if desired) can be added to the epoxy-clay mixture. Upon thorough mixing, the mixture can be cured under normal epoxy-anhydride curing conditions. The cured nanocomposites have demonstrated significant improvement in modulus before and after the glass transition temperature, and unexpected increased glass transition temperatures compared with the unfilled epoxy resin matrix polymers. Also, the nanocomposite demonstrated improved solvent and chemical resistance over a wide range of temperatures. X-ray diffraction was used to investigate the clay dispersion, intercalation and exfoliation in the cured nanocomposites.

[0067] The improved modulus, especially in the region near T_g, and elevated glass transition temperatures due to the nanocomposite formation are demonstrated in the DMA curves of FIGS. 1 and 2.

Example 1

[0068] This example demonstrates the preparation of organic quaternary onium ion-intercalated clays, which can be used to make the anhydride-cured epoxy nanocomposites.

Example 1A

[0069] 100 grams of Na-montmorillonite clay (PGW) commercially available from Nanocor, Inc. (Arlington Heights, IL) was dispersed in 3 liters of de-ionized water by mechanical paddle mixer or colloidal mill. The clay dispersion was heated to about 75°C to 80°C. 97.44 grams of octadecyltrimethyl ammonium chloride (Q-ST-50, 50 wt% solution from Tomah Products), was added to the clay dispersion followed by vigorous mixing. The mixture was maintained at about 75°C to 80°C for about 30 minutes, followed by a de-watering process, such as filtration. The filter cake was re-dispersed into 4 liters of water at about 75°C to 80°C and the solid was collected and placed into a 75°C to 80°C oven to dry followed by particle size reduction. The filter cake also can be freeze-dried. The dried material had a d₀₀₁ spacing of 24 Å as measured by X-ray diffraction and was coded as OD3M-PGW.

Example 1B

[0070] 100 grams of Na-montmorillonite clay (PGW) commercially available from Nanocor, Inc. (Arlington Heights, IL) was dispersed in 3 liters of de-ionized water by mechanical paddle mixer or colloidal mill. The clay dispersion was heated to about 75°C to 80°C. A solution of 67.2 g of Q182 in 1 liter of de-ionized water was introduced to the clay dispersion followed by vigorous mixing. The mixture was maintained at 75°C to 80°C for about 30 minutes, followed by a de-watering process, such as filtration. The filter cake was re-dispersed into 4 liters of 75°C to 80°C water and the solid was collected and placed into a 75°C to 80°C oven to dry followed by particle size reduction. The filter cake also can be freeze-dried. The dried material had a d001 spacing of 19 Å as measured by X-ray diffraction and was coded as **T50-PGW**.

Example 2

[0071] This example illustrates the intercalation of epoxy resins, and anhydride curing agents into the quaternary onium ion-intercalated clay galleries.

[0072] 5 grams of each of the onium ion-intercalated clays (**OD3M-PGW**, **T50-PGW**) were mixed separately with 45 grams of epoxy resin, DER331 at 75°C. The clay-epoxy dispersions were very stable at both 75°C and room temperature. 5 grams of the onium ion-intercalated clays was mixed with 45 grams of the anhydride curing agents, nadic methyl anhydride (NMA), hexahydrophalic anhydride (ECA-100) and (NMA) at room temperature. The clay-anhydride dispersions were stable after mixing, and had slight settle-down at extended storage time. However, the settle-down could be mixed well by gentle mixing before use. The resin-clay mixtures were each placed on a microscopic glass slide to measure X-ray diffraction patterns. The d001 spacing of each the intercalated clays in the resins are listed in Table 1.

Comparative Example 1

[0073] 5 grams of the non-onium ion-intercalated (PGW) clay was mixed with 45 grams of epoxy resin, DER331 at 75°C. The clay-epoxy dispersion was very stable at both 75°C and room temperature. 5 grams of the onium ion-intercalated clays of Example 1 (ODA- and Q182-intercalated) were mixed with 45 grams of the anhydride curing agents, nadic methyl anhydride (NMA), hexahydrophalic anhydride (ECA-100) and (NMA) at room temperature. The clay-anhydride dispersions were stable after mixing, and had slight settle-down at extended storage time. However, the settle-down could be mixed well by gentle mixing before use. The resin-clay mixtures were placed on a microscopic glass slide to measure X-ray diffraction patterns. The d001 spacings of the intercalated clays in the resins are listed in Table 1.

TABLE 1

d ₀₀₁ results of the treated clays dispersed in DER331, ECA 100, and NMA					
Examples	Clays	d ₀₀₁ (Å) Clay	d ₀₀₁ (Å) in DER331	d ₀₀₁ (Å) in ECA100	d ₀₀₁ (Å) in NMA
1	OD3M-PGW	24	37	34	36
1	T50-PGW	19	34	33	35
Comparative 1	PGW	13	13	13	13
Comparative 2	ODA-PGW	22	36	35	36
Comparative 3	Q182-PGW	25	38	33	35

Comparative Example 2

[0074] 100 grams of Na-montmorillonite clay (PGW) commercially available from Nanocor, Inc. (Arlington Heights, IL) was dispersed in 3 liters of de-ionized water by mechanical paddle mixer or colloidal mill. The clay dispersion was heated to about 75°C to 80°C. 37.8 grams of octadecyl-amine, available from Akzo Nobel, was mixed with 70 ml, 2 N HCl in 1 liter 75°C to 80°C de-ionized water. The amine-HCl solution was introduced to the clay dispersion, followed by vigorous mixing. The mixture was maintained at 75°C to 80°C for about 30 minutes, followed by a de-watering process, such as filtration. The filter cake was re-dispersed into 4 liters of 75°C to 80°C water and the solid was collected and placed into a 75°C to 80°C oven to dry followed by particle size reduction. The filter cake also can be freeze-dried.

The dried material has a d001 spacing of 22 Å as measured by X-ray diffraction and was coded as **ODA-PGW**.

[0075] 5 grams of the **ODA-PGW** intercalated clay was mixed with 45 grams of epoxy resin, DER331 at 75°C. The clay-epoxy dispersions were very stable at both 75 °C and room temperature. 5 grams of the onium ion-intercalated clay was mixed with 45 grams of each of the anhydride curing agents, nadic methyl anhydride (NMA), hexahydrophthalic anhydride (ECA-100) and (NMA) at room temperature. The clay-anhydride dispersions were stable after mixing, and had slight settle-down at extended storage time. However, the settle-down could be mixed well by gentle mixing before use. The resin-clay mixtures each were placed on a microscopic glass slide to measure X-ray diffraction patterns. The d001 spacings of the intercalated clays in the resins are listed in Table 1.

Comparative Example 3

[0076] 100 grams of Na-montmorillonite clay (PGW) commercially available from Nanocor, Inc. (Arlington Heights, IL) was dispersed in 3 liters of de-ionized water by mechanical paddle mixer or colloidal mill. The clay dispersion was heated to about 75°C to 80°C. 114.2 grams of octadecyl methyl bis-hydroxyethyl ammonium chloride (Q182, 50% solution), available from Tomah Products, was mixed with 1 liter of 75°C to 80°C de-ionized water. The Q182 solution was introduced to the clay dispersion followed by vigorous mixing. The mixture was maintained at about 75°C to 80°C for about 30 minutes, followed by a de-watering process, such as filtration. The filter cake was re-dispersed into 4 liters of 75°C to 80°C water and the solids were collected and placed into a 75°C to 80°C oven to dry followed by particle size reduction. The filter cake also can be freeze-dried. The dried material has a d001 spacing of 25 Å as measured by X-ray diffraction and was coded as **Q182-PGW**.

[0077] 5 grams of the **Q182-PGW** clay was mixed with 45 grams of epoxy resin, DER331 at 75°C. The clay-epoxy dispersions were very stable at both 75 °C and room temperature. 5 grams of the onium ion-intercalated clays were mixed with 45 grams of each of the anhydride curing agents, nadic methyl anhydride (NMA), hexahydrophthalic anhydride (ECA-100) and (NMA) at room temperature. The clay-anhydride dispersions were stable after mixing, and had slight settle-down at extended storage time. However, the settle-down could be mixed well by gentle mixing before use. The resin-clay mixtures each were placed on a microscopic glass slide to measure X-ray diffraction patterns. The d001 spacings of the intercalated clays in the resins are listed in Table 1.

Examples 3 and 4 and Comparative Examples 4-6

[0078] These examples demonstrate the formation of epoxy-anhydride-clay nanocomposites and their superior mechanical and thermal properties.

The preparation of unfilled cured resin matrix DER331

[0079] 100 grams of DER331 epoxy resin was mixed with 84 grams of ECA100 at 75°C. 1.5 grams of curing accelerator AP-6E (Dixie Chemicals) (benzyl trimethyl ammonium chloride solution) was added to the mixture. The mixture was then degassed and poured into an aluminum mold, which was coated with a mold releasing agent. The mixture was cured at 100°C for 1 hour, followed by an additional 4 hours at 160°C.

Preparation of DER331-ECA100-Clay nanocomposite with the onium ion-intercalated clays (**OD3M-PGW**, and **T50-PGW**) of Example 1

[0080] 5 grams of **OD3M-PGW** (10 phr) was mixed with 50 grams of DER331 at 75°C for several minutes. 42 grams of ECA 100 curing agent was added to the DER331-clay mixture and mixed thoroughly. 0.75 grams of the accelerator AP-6E was added to the mixture. The mixture was degassed and poured into an aluminum mold, which was coated with a mold releasing agent. The mixture was cured at 110°C for 1 hour, followed by additional 4 hours at 160°C. DER331-ECA100-clay nanocomposites with 10 phr T50-PGW (**Example 5**), 10 phr Q182-PGW (**Comparative Example 4**), 10 phr PGW (**Comparative Example 5**), and 10 phr ODA-PGW (**Comparative Example 6**) were prepared by the same method as the OD3M-PGW. Table 2 summarizes observations of the composite samples.

TABLE 2

Appearance of the composite samples in Examples 3 and 4 and Comparative Examples 4-6.		
Samples	Clay Treatment	Appearance
Neat DER331-ECA100	N/A	Light brown, transparent.

TABLE 2 (continued)

Appearance of the composite samples in Examples 3 and 4 and Comparative Examples 4-6.		
Samples	Clay Treatment	Appearance
Example 3	OD3M-PGW	Light brown, semi-transparent, no visible particles at x200.
Example 4	T50-PGW	Light brown, semi-transparent, no visible particles at x200.
Comparative Example 4	Q182-PGW	Light brown, semi-transparent, no visible particles at x200.
Comparative Example 5	PGW	Phase separated, visible clay particles settle on the bottom of the sample.
Comparative Example 6	ODA	No integrity, powdery.

Dynamic mechanical analysis (DMA) was used to evaluate the mechanical and thermal properties of the matrix and composite materials in these examples and comparative examples. The DMA experiments were carried out at 2°C/min. and 1 Hz. The DMA curves plot the storage modulus data at different temperatures. The glass transition temperature (T_g) was determined by the peak position of the Tan delta (the phase difference between the storage modulus and the lost modulus). FIG. 1 is the DMA curves of DER331-ECA 100 matrix and nanocomposite containing 10 phr OD3M-PGW. The storage modulus of the composite increases significantly in the testing temperature range. The T_g of nanocomposites increases to 140°C from the 120°C T_g of pure matrix polymer. Table 3 lists the storage modulus and T_g of the nanocomposites of these examples.

TABLE 3

Storage modulus and glass transition temperatures of the matrix and nanocomposites.					
		Modulus -20°C, MPa	Modulus 60°C, MPa	Modulus 120°C, MPa	T _g (°C)
Samples	Clay Treatment				
Neat DER331-ECA100	N/A	3.2	3.0	0.02	120
Example 3	OD3M-PGW	3.5	3.4	2.6	140
Example 4	T50-PGW	3.5	3.4	2.7	140
Comparative Example 4	Q182-PGW	3.2	3.0	1.6	130
Comparative Example 5	PGW	3.3	2.5	0.8	110
Comparative Example 6	ODA	failed	failed	failed	failed

[0081] The composites containing OD3M-PGW and T50-PGW have much better mechanical and thermal properties compared with the composites in the comparative examples. The glass transition temperatures of these composites were confirmed by using differential scanning calorimetry (DSC) or dynamic mechanical analysis (DMA).

Examples 5 and 6

[0082] These examples illustrate the different processing methods to prepare the nanocomposites.

[0083] In Example 5, 50 grams of DER331 epoxy resin was mixed with 42 grams of ECA100 curing agent at room temperature. Then 5 grams of OD3M-PGW was mixed with the premixed resin and curing agent. 0.75 grams of AP-6E curing accelerator was added to the mixture prior to degassing. The mixture was cured at 110°C for 1 hour, followed by an additional 4 hours at 160°C. DMA results of the nanocomposite of Example 5 are nearly identical to the DMA results from Example 3.

[0084] In Example 6, 5 grams of OD3M-PGW was mixed with 42 grams of ECA 100 curing agent at room temperature. Then, 50 grams of DER331 epoxy resin was introduced to the ECA 100-clay mixture. After being thoroughly mixed,

the mixture was added 0.75 grams of AP-6E. The mixture was cured at 110°C for 1 hour, followed by an additional 4 hours at 160°C. DMA results of the nanocomposite of Example 5 is nearly identical to the DMA results from Examples 3 and 5.

Examples 7-9 and Comparative Example 7

[0085] These examples illustrate the feature that intercalated clays of the present invention function as an accelerator for the anhydride-epoxy curing reaction.

[0086] In Comparative Example 7, a mixture of 50 grams of DER331 epoxy resin and 42 grams of ECA 100 curing agent was evaluated at 110°C for 1 hour, followed by an additional 4 hours at 160°C. No curing occurred during the heating time, except slight oxidation of the resin mixture.

[0087] Examples 7-9 demonstrate that the OD3M-PGW, and T50-PGW clays function as an accelerator in the DER331-ECA100 curing reaction. The resin-clay (DER331-ECA100-OD3M-PGW) mixtures were prepared according to Examples 3, 5 and 6, but without adding the AP-6E curing accelerator. The mixture was cured at the same conditions as with the accelerator at 110°C for 1 hour, followed by an additional 4 hours at 160°C. All mixtures were cured very well. DMA test results indicate the composites in Examples 7-9 have comparable mechanical and thermal properties to those in Examples 3, 5 and 6. DMA curves of Example 3 and Example 7 are shown in FIG. 2.

Examples 10 and 11

[0088] These examples demonstrate the superior mechanical and thermal performance of the DER331-NMA resin based anhydride-cured epoxy composites.

[0089] The nanocomposites were prepared by the above-mentioned methods. The nanocomposites with 10 phr OD3M-PGW (Example 10) and 10 phr T50-PGW (Example 11) have significantly improved storage modulus and increased glass transition temperature.

[0090] The following describes a number of alternative embodiments of the invention, but the embodiments are part of the description:-

1. A nanocomposite composition comprising about 0.05 weight percent to about 60 weight percent of a layered silicate material intercalated with an onium ion spacing agent and about 40 weight percent to about 99.95 weight percent of a matrix polymer comprising an anhydride-curable epoxy resin that is not covalently bonded to the layered silicate material or to the onium ion spacing agent, wherein the intercalated layered silicate material is dispersed uniformly throughout the matrix polymer.

2. A nanocomposite composition in accordance with item 1, wherein the matrix polymer is co-intercalated into the layered silicate material.

3. A nanocomposite composition in accordance with item 2, wherein the matrix polymer is co-intercalated into the layered silicate material while dispersing the layered material throughout the matrix polymer.

4. A nanocomposite composition in accordance with item 2, wherein the matrix polymer is co-intercalated into the layered silicate material prior to dispersing the layered silicate material throughout the matrix polymer.

5. A nanocomposite material in accordance with item 1, wherein the onium ions include at least one moiety covalently bonded to a positively charged nitrogen atom that has a length of at least six carbon atoms.

6. A nanocomposite composition in accordance with item 1 formed by contacting a phyllosilicate with intercalant onium ions to form an intercalating composition, having a molar ratio of onium ions:phyllosilicate interlayer exchangeable cations of at least about 0.25:1 to achieve sorption of the onium ions between adjacent spaced layers of the phyllosilicate to expand the spacing between a predominance of the adjacent phyllosilicate platelets at least about 3 Å, when measured after sorption of the onium ions, and a second intercalant disposed between adjacent spaced layers of the phyllosilicate material to space the adjacent phyllosilicate an additional at least 3 Å, said second intercalant comprising an anhydride-curable epoxy resin that is not covalently bonded to the layered silicate material or to the onium ion spacing agent, wherein the intercalated layered silicate material is uniformly dispersed throughout the matrix polymer.

7. A composition in accordance with item 6, wherein the intercalated phyllosilicate is exfoliated into a predominance of individual platelets.

8. A composition in accordance with item 6, wherein the molar ratio of intercalant onium ions:phyllosilicate interlayer exchangeable cations is at least 30 mole percent, based on the number of moles of interlayer exchangeable cations in the phyllosilicate.

9. A composition in accordance with item 8, wherein the molar ratio of intercalant onium ions:phyllosilicate interlayer exchangeable cations is at least 50 mole percent.

10. A nanocomposite concentrate composition comprising about 10% by weight to about 90% by weight of a layered silicate material intercalated with a polymer or oligomer of an anhydride-curable epoxy resin that is not covalently bonded to the layered silicate material, and about 10 weight percent to about 90 weight percent of a matrix polymer comprising an anhydride-curable epoxy resin, wherein the intercalated layered silicate material is dispersed uniformly throughout the matrix polymer.

11. A nanocomposite composition in accordance with item 10, wherein the matrix polymer is intercalated into the layered silicate material.

12. A nanocomposite composition in accordance with item 11, wherein the matrix polymer is intercalated into the layered silicate material while dispersing the layered material throughout the matrix polymer.

13. A nanocomposite composition in accordance with item 11, wherein the matrix polymer is intercalated into the layered silicate material prior to dispersing the layered silicate material throughout the matrix polymer.

14. A nanocomposite composition in accordance with item 10, wherein prior to intercalating the layered material with the anhydride-curable epoxy resin, the layered silicate material is first intercalated with onium ions that include at least one moiety covalently bonded to a protonated nitrogen atom that has a length of at least six carbon atoms.

15. A method of intercalating a phyllosilicate comprising:

contacting the phyllosilicate with an intercalating composition comprising at least a 0.25:1 molar ratio of onium ion cations to phyllosilicate interlayer exchangeable cations, to achieve intercalation of, and ion-exchange of said onium ion cations with said interlayer cations, between said adjacent phyllosilicate platelets in an amount sufficient to space said adjacent phyllosilicate platelets at least about 3 Å; and

co-intercalating the onium ion-intercalated layered silicate material with an anhydride-curable epoxy resin that is not covalently bonded to the layered silicate material or to the onium ion cations.

16. The method of item 15, wherein said intercalating composition includes a water carrier comprising about 5% to about 50% by weight water, based on the dry weight of said phyllosilicate.

17. The method of item 15, wherein the anhydride-curable epoxy resin is co-intercalated into the layered silicate material by co-intercalating an anhydride-curable epoxy resin, or its monomer reactants capable of polymerization to form an anhydride-curable epoxy resin.

18. The method of item 17, wherein the epoxy resin intercalant is included in an intercalating composition in a concentration of about 10-100% by weight, based on the dry weight of the phyllosilicate.

19. A method in accordance with item 15, wherein the onium ion-intercalated phyllosilicate is co-intercalated with a second intercalant selected from the group consisting of a polymerizable monomer, a polymerizable oligomer, a polymer, and a mixture thereof, said second intercalant being an anhydride-curable epoxy resin, or monomer reactants capable of polymerization to form an anhydride-curable epoxy resin, to further expand the spacing between a predominance of the adjacent phyllosilicate platelets at least an additional 3 Å; and (c) dispersing the co-intercalated layered silicate material throughout the matrix polymer.

20. A method of manufacturing a composite material in accordance with item 19, wherein the intercalate is dispersed throughout said matrix polymer to achieve intercalation of a portion of the matrix polymer between the phyllosilicate platelets, in an amount sufficient to space said adjacent phyllosilicate platelets said additional at least 3 Å.

21. A method in accordance with item 20, wherein the matrix polymer is co-intercalated into the layered silicate material prior to dispersing the layered silicate material throughout the matrix polymer.

22. A method in accordance with item 20, wherein the matrix polymer is co-intercalated into the layered silicate material while dispersing the layered material throughout the matrix polymer.

23. A method in accordance with item 20, wherein the onium ions include at least one moiety covalently bonded to a protonated nitrogen atom that has a length of at least six carbon atoms.

24. A method in accordance with item 20, further including the step of adding an anhydride curing agent to said matrix polymer for intercalating a portion of the anhydride curing agent into the phyllosilicate together with the intercalation of the matrix polymer.

25. A method in accordance with item 24, further including the step of adding a curing accelerator to the matrix polymer for intercalation of a portion of the curing accelerator into the phyllosilicate together with the matrix polymer.

26. A method in accordance with item 20, further including the step of adding an anhydride curing agent to the matrix polymer prior to dispersing said onium ion-intercalated phyllosilicate throughout the matrix polymer.

27. A method in accordance with item 20, further including the step of mixing the onium ion-intercalated phyllosilicate with the anhydride-curable epoxy resin and then adding the anhydride curing agent to the mixture.

28. A method in accordance with item 27, further including the step of adding a curing accelerator to the mixture of the onium ion-intercalated phyllosilicate and the epoxy resin.

29. A method in accordance with item 20, further including the step of adding an anhydride curing agent to the onium ion-intercalated phyllosilicate prior to dispersing the intercalate throughout the matrix polymer.

30. A method in accordance with item 29, further including the step of adding a curing accelerator to the onium ion-intercalated phyllosilicate prior to dispersing the intercalate throughout the matrix polymer.

31. The method of item 20, wherein said phyllosilicate is contacted with said intercalant onium ions, said phyllosilicate, and an anhydride-curable epoxy resin, wherein the concentration of the onium ions is in a molar ratio of onium ions:phyllosilicate interlayer exchangeable cations of at least 0.25:1.

32. The method of item 31, wherein said phyllosilicate is contacted with said intercalant onium ions, said phyllosilicate, and an anhydride-curable epoxy resin, wherein the concentration of the onium ions is in a molar ratio of onium ions:phyllosilicate interlayer exchangeable cations of at least 0.5:1.

33. The method of item 32, wherein said phyllosilicate is contacted with said intercalant onium ions, said phyllosilicate, and an anhydride-curable epoxy resin, wherein the concentration of the onium ions is in a molar ratio of onium ions:phyllosilicate interlayer exchangeable cations of at least 1:1.

34. A method in accordance with item 19, wherein the molar ratio of onium ions:phyllosilicate interlayer cations of at least 0.25:1;

combining the intercalated phyllosilicate with a thermoplastic or thermosetting polymer, and heating the thermoplastic polymer sufficiently to provide for flow of said thermoplastic polymer; and

dispersing said intercalated phyllosilicate throughout said matrix polymer.

35. A method in accordance with item 34, wherein the intercalating composition includes about 10% to about 200% by weight of said anhydride-curable epoxy resin intercalant, based on the dry weight of phyllosilicate contacted by said intercalating composition.

36. A method in accordance with item 34, wherein the amount of intercalant onium ion spacing/coupling agent intercalated into the phyllosilicate material is in a molar ratio of at least 1:1, onium ions: exchangeable cations in the interlayer spaces of the phyllosilicate material.

37. A method in accordance with item 36, wherein the molar ratio of intercalated onium ion spacing/coupling agent to interlayer phyllosilicate cations is from about 1:1 to about 1:5.

38. A method in accordance with item 34, wherein the weight ratio of the epoxy intercalant to phyllosilicate material, dry basis, is from about 20 grams of epoxy intercalant per 100 grams of phyllosilicate material to about 200 grams of epoxy intercalant per 100 grams of phyllosilicate material.

39. A method in accordance with item 34, wherein the epoxy oligomer or polymer is intercalated into the phyllosilicate by melting the epoxy oligomer or polymer and dispersing the phyllosilicate throughout the epoxy melt.

40. A method in accordance with item 39, wherein said dispersing is accomplished in an extruder.

41. A method of manufacturing the nanocomposite composition of item 1 comprising intercalating the phyllosilicate material with an onium ion spacing agent by contacting the phyllosilicate with onium ions in a molar ratio of onium ions:phyllosilicate interlayer exchangeable cations of at least 0.25:1;


forming a mixture of the intercalated phyllosilicate material with an anhydride-curable epoxy resin; and

subjecting the mixture to conditions sufficient to react and polymerize the anhydride-curable epoxy resin with an anhydride curing agent for the epoxy resin to cure the epoxy resin while in contact with the intercalated phyllosilicate and to co-intercalate the epoxy resin between adjacent platelets of the phyllosilicate material, wherein the anhydride-curable epoxy resin is combined in amounts such that the resulting composite material contains 40% to 99.95% oligomer or polymer and 0.05% to 60% intercalated phyllosilicate.

42. A method in accordance with item 41, wherein the second intercalant is an anhydride-curable epoxy resin, or monomer reactants capable of polymerization to form an anhydride-curable epoxy resin.

Claims

1. A nanocomposite composition comprising 0.05 weight percent to 60 weight percent of a layered silicate material intercalated with a quaternary onium ion spacing agent having the structure



wherein X=N, P, O or S and R₁, R₂, R₃ and R₄, are the same or different, and each represent an epoxy non-reactive organic radical; and

40 weight percent to 99.95 weight percent of a matrix polymer comprising an anhydride-cured epoxy resin that is not covalently bonded to the layered silicate material or to the onium ion spacing agent, wherein the intercalated layered silicate material is dispersed uniformly throughout the matrix polymer.

2. A nanocomposite composition as claimed in claim 1, wherein the quaternary onium ions include at least one moiety covalently bonded to a positively charged nitrogen atom that has a length of at least six carbon atoms.
3. A nanocomposite composition as claimed in claim 1 or 2, formed by contacting a phyllosilicate with intercalant quaternary onium ions to form an intercalating composition, having a molar ratio of quaternary onium ions: phyllosilicate interlayer exchangeable cations of at least 0.25:1 to achieve sorption of the quaternary onium ions between adjacent spaced layers of the phyllosilicate to expand the spacing between a predominance of the adjacent phyllosilicate platelets at least 3 Å, when measured after sorption of the quaternary onium ions, and a second intercalant disposed between adjacent spaced layers of the phyllosilicate material to space the adjacent phyllosilicate

icate an additional at least 3 Å, said second intercalant comprising an anhydride-cured epoxy resin that is not covalently bonded to the layered silicate material or to the quaternary onium ion spacing agent, wherein the intercalated layered silicate material is uniformly dispersed throughout the matrix polymer.

4. A composition as claimed in claim 3, wherein the intercalated phyllosilicate is exfoliated into a predominance of individual platelets.
5. A composition as claimed in claim 3 or 4, wherein the molar ratio of intercalant quaternary onium ions: phyllosilicate interlayer exchangeable cations is at least 30 mole percent, based on the number of moles of interlayer exchangeable cations in the phyllosilicate.
6. A composition as claimed in claim 5, wherein the molar ratio of intercalant quaternary onium ions: phyllosilicate interlayer exchangeable cations is at least 50 mole percent.
7. A nanocomposite concentrate composition comprising 10% by weight to 90% by weight of a layered silicate material intercalated with a polymer or oligomer of an anhydride-cured epoxy resin that is not covalently bonded to the layered silicate material, and 10 weight percent to 90 weight percent of a matrix polymer comprising an anhydride-cured epoxy resin, wherein the intercalated layered silicate material is dispersed uniformly throughout the matrix polymer.
8. A nanocomposite composition as claimed in claim 7, wherein prior to intercalating the layered material with the anhydride-cured epoxy resin, the layered silicate material is first intercalated with quaternary onium ions that include at least one moiety covalently bonded to a protonated nitrogen atom that has a length of at least six carbon atoms.
9. A nanocomposite composition as claimed in any one of the preceding claims, wherein the matrix polymer is co-intercalated into the layered silicate material.
10. A nanocomposite composition as claimed in claim 9, wherein the matrix polymer is co-intercalated into the layered silicate material while dispersing the layered material throughout the matrix polymer.
11. A nanocomposite composition as claimed in claim 9, wherein the matrix polymer is co-intercalated into the layered silicate material prior to dispersing the layered silicate material throughout the matrix polymer.
12. A method of intercalating a phyllosilicate comprising:

contacting the phyllosilicate with an intercalating composition comprising at least a 0.25:1 molar ratio of quaternary onium ion cations to phyllosilicate interlayer exchangeable cations, to achieve intercalation of, and ion-exchange of said quaternary onium ion cations with said interlayer cations, between said adjacent phyllosilicate platelets in an amount sufficient to space said adjacent phyllosilicate platelets at least 3Å; and co-intercalating the quaternary onium ion-intercalated layered silicate material with an anhydride-curable epoxy resin that is not covalently bonded to the layered silicate material or to the quaternary onium ion cations, and an anhydride curing agent for the epoxy resin.
13. A method as claimed in claim 12, wherein said intercalating composition includes a water carrier comprising 5% to 50% by weight water, based on the dry weight of said phyllosilicate.
14. A method as claimed in claim 12 or 13, wherein the anhydride-curable epoxy resin is co-intercalated into the layered silicate material by co-intercalating an anhydride-curable epoxy resin, or its monomer reactants capable of polymerization to form an anhydride-curable epoxy resin.
15. A method as claimed in claim 14, wherein the epoxy resin intercalant is included in an intercalating composition in a concentration of 10-100% by weight, based on the dry weight of the phyllosilicate.
16. A method of making a composition as claimed in any one of claims 1 to 11, wherein the quaternary onium ion-intercalated phyllosilicate as claimed in any one of claims 12 to 15, is co-intercalated with a second intercalant selected from the group consisting of a polymerizable monomer, a polymerizable oligomer, a polymer, and a mixture thereof, said second intercalant being an anhydride curing agent and an anhydride-curable epoxy resin, or mon-

omer reactants capable of polymerization to form an anhydride-curable epoxy resin, to further expand the spacing between a predominance of the adjacent phyllosilicate platelets at least an additional 3Å and dispersing the co-intercalated layered silicate material throughout the matrix polymer.

- 5 17. A method as claimed in claim 16, wherein the intercalate is dispersed throughout said matrix polymer to achieve intercalation of a portion of the matrix polymer between the phyllosilicate platelets, in an amount sufficient to space said adjacent phyllosilicate platelets said additional at least 3Å.
- 10 18. A method as claimed in claim 16 or 17, wherein the quaternary onium ions include at least one moiety covalently bonded to a nitrogen atom that has a length of at least six carbon atoms.
- 15 19. A method as claimed in any one of claims 12 to 18, further including the step of adding a curing accelerator to the anhydride-curable epoxy resin for intercalation of a portion of the curing accelerator into the phyllosilicate together with the anhydride-curable epoxy resin.
- 20 20. A method as claimed in any one of claims 12 to 19, wherein the matrix polymer is an anhydride-curable epoxy resin, and further including the step of adding an anhydride curing agent to the matrix polymer prior to dispersing said quaternary onium ion-intercalated phyllosilicate throughout the matrix polymer.
- 25 21. A method as claimed in any one of claims 12 to 20, further including the step of mixing the quaternary onium ion-intercalated phyllosilicate with the anhydride-curable epoxy resin and then adding the anhydride curing agent to the mixture.
- 30 22. A method as claimed in claim 21, further including the step of adding a curing accelerator to the mixture of the quaternary onium ion-intercalated phyllosilicate and the epoxy resin.
- 35 23. A method as claimed in any one of claims 12 to 22, further including the step of adding an anhydride curing agent to the quaternary onium ion-intercalated phyllosilicate prior to dispersing the intercalate throughout the anhydride-curable epoxy resin.
- 40 24. A method as claimed in claim 23, further including the step of adding a curing accelerator to the quaternary onium ion-intercalated phyllosilicate prior to dispersing the intercalate throughout the anhydride-curable epoxy resin.
- 45 25. A method as claimed in any one of claims 16 to 24, wherein said phyllosilicate is contacted with said intercalant quaternary onium ions, and an anhydride-curable epoxy resin, wherein the concentration of the quaternary onium ions is in a molar ratio of quaternary onium ions: phyllosilicate interlayer exchangeable cations of at least 0.25:1.
- 50 26. A method as claimed in claim 25, wherein said phyllosilicate is contacted with said intercalant quaternary onium ions, and an anhydride-curable epoxy resin, wherein the concentration of the quaternary onium ions is in a molar ratio of quaternary onium ions: phyllosilicate interlayer exchangeable cations of at least 0.5:1.
- 55 27. A method as claimed in claim 26, wherein said phyllosilicate is contacted with said intercalant quaternary onium ions, and an anhydride-curable epoxy resin, and an anhydride curing agent wherein the concentration of the quaternary onium ions is in a molar ratio of quaternary onium ions: phyllosilicate interlayer exchangeable cations of at least 1:1.
28. A method as claimed in any one of claims 16 to 27, wherein the molar ratio of quaternary onium ions: phyllosilicate interlayer cations of at least 0.25:1;
combining the intercalated phyllosilicate with an intercalating composition comprising a thermoplastic or thermosetting polymer, and heating the thermoplastic polymer sufficiently to provide for flow of said thermoplastic polymer; and
dispersing said intercalated phyllosilicate through an anhydride-curable epoxy matrix polymer.
29. A method as claimed in claim 28, wherein the intercalating composition includes 10% to 200% by weight of said anhydride-curable epoxy resin intercalant, based on the dry weight of phyllosilicate contacted by said intercalating composition.

30. A method as claimed in claim 28 or 29, wherein the amount of intercalant quaternary onium ion spacing/coupling agent intercalated into the phyllosilicate material is in a molar ratio of at least 1:1, quaternary onium ions: exchangeable cations in the interlayer spaces of the phyllosilicate material.

31. A method as claimed in claim 30, wherein the molar ratio of intercalated quaternary onium ion spacing/coupling agent to interlayer phyllosilicate cations is from 1:1 to 1:5.

32. A method as claimed in any one of claims 28 to 31, wherein the weight ratio of the thermoplastic or thermosetting polymer intercalant to phyllosilicate material, dry basis, is from 20 grams of epoxy intercalant per 100 grams of phyllosilicate material to 200 grams of epoxy intercalant per 100 grams of phyllosilicate material.

33. A method as claimed in any one of claims 28 to 32, wherein the polymer intercalant is an epoxy oligomer or polymer intercalated into the phyllosilicate by melting the epoxy oligomer or polymer and dispersing the phyllosilicate throughout the epoxy melt.

34. A method as claimed in claim 33, wherein said dispersing is accomplished in an extruder.

35. A method of manufacturing the nanocomposite composition as claimed in any one of claims 1 to 6, comprising intercalating the phyllosilicate material with a quaternary onium ion spacing agent by contacting the phyllosilicate with quaternary onium ions in a molar ratio of quaternary onium ions: phyllosilicate interlayer exchangeable cations of at least 0.25:1;


forming a mixture of the intercalated phyllosilicate material with an anhydride curing agent and an anhydride-curable epoxy resin second intercalant; and

subjecting the mixture to conditions sufficient to react and polymerize the anhydride-curable epoxy resin with an anhydride curing agent for the epoxy resin to cure the epoxy resin while in contact with the intercalated phyllosilicate and to co-intercalate the epoxy resin between adjacent platelets of the phyllosilicate material, wherein the anhydride-curable epoxy resin is combined in amounts such that the resulting composite material contains 40% to 99.95% epoxy oligomer or polymer and 0.05% to 60% intercalated phyllosilicate.

36. A method as claimed in claim 35, wherein the second intercalant is an anhydride-curable epoxy resin, or monomer reactants capable of polymerization to form an anhydride-curable epoxy resin.

Patentansprüche

1. Nanocomposite-Zusammensetzung umfassend 0,05 Gew.-% bis 60 Gew.-% eines geschichteten Silikatmaterials, das mit einem quartären Oniumionen-Abstandsmittel interkaliert ist, die die Struktur



aufweist, worin X = N, P, O oder S und R₁, R₂, R₃ und R₄ gleich oder unterschiedlich sind und jedes ein nicht-reaktives organisches Epoxidradikal darstellt; und

40 Gew.-% bis 99,95 Gew.-% eines Matrixpolymers, umfassend ein Anhydrid-gehärtetes Epoxidharz, das nicht kovalent an das geschichtete Silikatmaterial oder an das Oniumionen-Abstandsmittel gebunden ist, worin das interkalierte geschichtete Silikatmaterial gleichmäßig durch das gesamte Matrixpolymer hindurch dispergiert ist.

2. Nanocomposite-Zusammensetzung nach Anspruch 1, worin die quartären Oniumionen mindestens eine an ein positiv geladenes Stickstoffatom kovalent gebundene Komponente einschließen, die eine Länge von mindestens sechs Kohlenstoffatomen aufweist.

3. Nanocomposite-Zusammensetzung nach Anspruch 1 oder 2, die wie folgt gebildet wird: durch Kontaktieren eines

Phyllosilikats mit einem Interkalationsmittel aus quartären Oniumionen zur Bildung einer Interkalationszusammensetzung, die ein Molverhältnis von quartären Oniumionen : austauschbaren Kationen in der Phyllosilikat-Zwischenschicht von mindestens 0,25 : 1 zum Erreichen einer Sorption der quartären Oniumionen zwischen benachbarten, mit Abstand angeordneten Schichten des Phyllosilikats zum Expandieren des Abstands zwischen einer Überzahl der benachbarten Phyllosilikat-Blättchen um mindestens 3 Å, wenn nach der Sorption der quartären Oniumionen gemessen, und einem zweiten Interkalationsmittel, das zwischen benachbarten mit Abstand angeordneten Schichten des Phyllosilikatmaterials abgelagert ist, um das benachbarte Phyllosilikat mit einem zusätzlichen Abstand von mindestens 3 Å anzuordnen, wobei genanntes zweites Interkalationsmittel ein Anhydrid-gehärtetes Epoxidharz umfasst, das nicht kovalent an das geschichtete Silikatmaterial oder an das Abstandsmittel aus quartären Oniumionen gebunden ist, worin das interkalierte geschichtete Silikatmaterial gleichmäßig durch das gesamte Matrixpolymer dispergiert ist.

4. Zusammensetzung nach Anspruch 3, worin das interkalierte Phyllosilikat in eine Überzahl individueller Blättchen exfoliert ist.

5. Zusammensetzung nach Anspruch 3 oder 4, worin das Molverhältnis des Interkalationsmittels aus quartären Oniumionen : austauschbaren Kationen in der Phyllosilikat-Zwischenschicht bezogen auf die Anzahl von Molen austauschbarer Kationen im Phyllosilikat in der Zwischenschicht mindestens 30 Mol-% beträgt.

6. Zusammensetzung nach Anspruch 5, worin das Molverhältnis des Interkalationsmittels aus quartären Oniumionen : austauschbaren Kationen in der Phyllosilikat-Zwischenschicht mindestens 50 Mol-% beträgt.

7. Nanocomposite-Konzentratzusammensetzung umfassend 10 Gew.-% bis 90 Gew.-% eines geschichteten Silikatmaterials, das mit einem Polymer oder Oligomer eines Anhydrid-gehärteten Epoxidharzes, das nicht kovalent an das geschichtete Silikatmaterial gebunden ist, interkaliert ist, und 10 Gew.-% bis 90 Gew.-% eines Matrixpolymers umfassend ein Anhydrid-gehärtetes Epoxidharz, worin das interkalierte geschichtete Silikatmaterial gleichmäßig durch das gesamte Matrixpolymer hindurch dispergiert ist.

8. Nanocomposite-Zusammensetzung nach Anspruch 7, worin vor dem Interkalieren des geschichteten Materials mit dem Anhydrid-gehärteten Epoxidharz das geschichtete Silikatmaterial zuerst mit quartären Oniumionen interkaliert wird, die mindestens eine kovalent an ein protoniertes Stickstoffatom gebundene Komponente einschließt, die eine Länge von mindestens sechs Kohlenstoffatomen aufweist.

9. Nanocomposite-Zusammensetzung nach einem der vorangehenden Ansprüche, worin das Matrixpolymer mit in das geschichtete Silikatmaterial interkaliert ist.

10. Nanocomposite-Zusammensetzung nach Anspruch 9, worin das Matrixpolymer mit in das geschichtete Silikatmaterial interkaliert wird, während das geschichtete Material durch das gesamte Matrixpolymer hindurch dispergiert wird.

11. Nanocomposite-Zusammensetzung nach Anspruch 9, worin das Matrixpolymer vor dem Dispergieren des geschichteten Silikatmaterials durch das gesamte Matrixpolymer hindurch mit in das geschichtete Silikatmaterial interkaliert wird.

12. Verfahren zum Interkalieren eines Phyllosilikats umfassend:

Kontaktieren des Phyllosilikats mit einer Interkalationszusammensetzung umfassend mindestens ein Molverhältnis von 0,25 : 1 der quartären Oniumion-Kationen zu austauschbaren Kationen in der Phyllosilikat-Zwischenschicht zum Erreichen der Interkalation von und Ionenaustausch von genannten quartären Oniumion-Kationen mit genannten Zwischenschichtkationen zwischen genannten benachbarten Phyllosilikat-Blättchen in einer ausreichenden Menge, um genannte benachbarte Phyllosilikat-Blättchen mit einem Abstand von mindestens 3 Å anzuordnen; und

das miteinander Interkalieren des quartären Oniumion-interkalierten geschichteten Silikatmaterials mit einem Anhydrid-härtbaren Epoxidharz, das nicht kovalent an das geschichtete Silikatmaterial oder an die quartären Oniumion-Kationen gebunden ist und ein Anhydrid-Härtungsmittel für das Epoxidharz.

13. Verfahren nach Anspruch 12, worin die genannte Interkalationszusammensetzung einen Wasserträger, umfassend

5 Gew.-% bis 50 Gew.-% Wasser bezogen auf das Trockengewicht von genanntem Phyllosilikat einschließt.


14. Verfahren nach Anspruch 12 oder 13, worin das Anhydrid-härtbare Epoxidharz in das geschichtete Silikatmaterial durch miteinander Interkalieren eines Anhydrid-härtbaren Epoxidharzes miteinander interkaliert ist, oder seine Monomer-Reaktanten zur Polymerisation zur Bildung eines Anhydrid-härtbaren Epoxidharzes fähig sind.
15. Verfahren nach Anspruch 14, worin das Epoxidharz-Interkalationsmittel in eine Interkalationszusammensetzung in einer Konzentration von 10 - 100 Gew.-% bezogen auf das Trockengewicht des Phyllosilikats eingeschlossen ist.
16. Verfahren zur Herstellung einer Zusammensetzung nach einem der Ansprüche 1 bis 11, worin das mit quartärem Oniumion-interkalierte Phyllosilikat nach einem der Ansprüche 12 bis 15 mit einem zweiten Interkalationsmittel, das aus der Gruppe ausgewählt ist, bestehend aus einem polymerisierbaren Monomer, einem polymerisierbaren Oligomer, einem Polymer, und Gemischen davon, miteinander interkaliert wird, wobei das zweite Interkalationsmittel ein Anhydrid-härtendes Mittel und ein Anhydrid-härtbares Epoxidharz oder Monomer-Reaktanten darstellt, die zur Polymerisation zur Bildung eines Anhydrid-härtbaren Epoxidharzes fähig sind, um den Abstand zwischen einer Überzahl benachbarter Phyllosilikat-Blättchen um mindestens zusätzliche 3 Å weiter zu expandieren und das miteinander interkalierte geschichtete Silikatmaterial durch das gesamte Matrixpolymer hindurch zu dispergieren.
17. Verfahren nach Anspruch 16, worin das Interkalat durch genanntes Matrixpolymer hindurch zum Erreichen einer Interkalation eines Anteils des Matrixpolymers zwischen den Phyllosilikat-Blättchen in einer Menge dispergiert wird, die ausreicht, um genannte benachbarte Phyllosilikat-Blättchen mit einem Abstand von genannten zusätzlich mindestens 3 Å anzuordnen.
18. Verfahren nach Anspruch 16 oder 17, worin die quartären Oniumionen mindestens eine kovalent an ein Stickstoffatom gebundene Komponente einschließen, die eine Länge von mindestens sechs Kohlenstoffatomen aufweist.
19. Verfahren nach einem der Ansprüche 12 bis 18, das weiter den Schritt des Zufügens eines Härtingsbeschleunigers zum Anhydrid-härtbaren Epoxidharz zur Interkalation eines Anteils des Härtingsbeschleunigers in das Phyllosilikat zusammen mit dem Anhydrid-härtbaren Epoxidharz einschließt.
20. Verfahren nach einem der Ansprüche 12 bis 19, worin das Matrixpolymer ein Anhydrid-härtbares Epoxidharz darstellt und weiter den Schritt des Zufügens eines Anhydrid-Härtungsmittels zum Matrixpolymer vor dem Dispergieren des genannten quartären Oniumion-interkalierten Phyllosilikats durch das gesamte Matrixpolymer hindurch einschließt.
21. Verfahren nach einem der Ansprüche 12 bis 20, das weiter den Schritt des Mischens des quartären Oniumion-interkalierten Phyllosilikats mit dem Anhydrid-härtbaren Epoxidharz und dann Zufügen des Anhydrid-Härtungsmittels zum Gemisch einschließt.
22. Verfahren nach Anspruch 21, das weiter den Schritt des Zufügens eines Härtingsbeschleunigers zum Gemisch aus dem quartären Oniumion-interkalierten Phyllosilikat und dem Epoxidharz einschließt.
23. Verfahren nach einem der Ansprüche 12 bis 22, das weiter den Schritt des Zufügens eines Anhydrid-Härtungsmittels zum quartären Oniumion-interkalierten Phyllosilikat vor dem Dispergieren des Interkalats durch das gesamte Anhydrid-härtbare Epoxidharz hindurch einschließt.
24. Verfahren nach Anspruch 23, das weiter den Schritt des Zufügens eines Härtingsbeschleunigers zum quartären Oniumion-interkalierten Phyllosilikat vor dem Dispergieren des Interkalats durch das gesamte Anhydrid-härtbare Epoxidharz hindurch einschließt.
25. Verfahren nach einem der Ansprüche 16 bis 24, worin genanntes Phyllosilikat mit genanntem Interkalationsmittel aus quartären Oniumionen und einem Anhydrid-härtbaren Epoxidharz kontaktiert wird, worin die Konzentration der quartären Oniumionen in einem Molverhältnis von quartären Oniumionen : austauschbaren Kationen in der Phyllosilikat-Zwischenschicht von mindestens 0,25 : 1 beträgt.
26. Verfahren nach Anspruch 25, worin genanntes Phyllosilikat mit genanntem Interkalationsmittel aus quartären Oniumionen und einem Anhydrid-härtbaren Epoxidharz kontaktiert wird, worin die Konzentration der quartären Oniumionen

umionen in einem Molverhältnis von quartären Oniumionen : austauschbaren Kationen in der Phyllosilikat-Zwischenschicht von mindestens 0,5 : 1 vorliegt.

27. Verfahren nach Anspruch 26, worin genanntes Phyllosilikat mit genanntem Interkalationsmittel aus quartären Oniumionen und einem Anhydrid-härtbaren Epoxidharz und einem Anhydrid-Härtungsmittel kontaktiert wird, worin die Konzentration der quartären Oniumionen in einem Molverhältnis von quartären Oniumionen: austauschbaren Kationen in der Phyllosilikat-Zwischenschicht von mindestens 1 : 1 vorliegt.
28. Verfahren nach einem der Ansprüche 16 bis 27, worin das Molverhältnis der quartären Oniumionen : Kationen in der Phyllosilikat-Zwischenschicht mindestens 0,25 : 1 beträgt;
Kombinieren des interkalierten Phyllosilikats mit einer Interkalationszusammensetzung, umfassend ein thermoplastisches oder duroplastisches Polymer und ausreichendes Erhitzen des thermoplastischen Polymers zur Bereitstellung des Fließens von genanntem thermoplastischem Polymer; und
Dispergieren des genannten interkalierten Phyllosilikats durch ein Anhydrid-härtbares Epoxid-Matrixpolymer hindurch.
29. Verfahren nach Anspruch 28, worin die Interkalationszusammensetzung 10 Gew.-% bis 200 Gew.-% von genanntem Interkalationsmittel aus Anhydrid-härtbarem Epoxidharz bezogen auf das Trockengewicht von Phyllosilikat, das durch genannte Interkalationszusammensetzung kontaktiert wird, einschließt.
30. Verfahren nach Anspruch 28 oder 29, worin die Menge des Abstandsmittels/Haftvermittlers für die quartären Oniumionen im Interkalationsmittel, das in das Phyllosilikatmaterial interkaliert ist, in einem Molverhältnis von mindestens 1 : 1, quartären Oniumionen : austauschbaren Kationen in den Zwischenschichtabständen des Phyllosilikatmaterials liegt.
31. Verfahren nach Anspruch 30, worin das Molverhältnis von Abstandsmittel/Haftvermittler für die interkalierten quartären Oniumionen zu Phyllosilikatkationen in der Zwischenschicht von 1 : 1 bis 1 : 5 beträgt.
32. Verfahren nach einem der Ansprüche 28 bis 31, worin das Gewichtsverhältnis des Interkalationsmittels aus thermoplastischem oder duroplastischem Polymer zu Phyllosilikatmaterial, Trockenbasis, von 20 g Epoxid-Interkalationsmittel pro 100 g Phyllosilikatmaterial zu 200 g Epoxid-Interkalationsmittel pro 100 g Phyllosilikatmaterial beträgt.
33. Verfahren nach einem der Ansprüche 28 bis 32, worin das Polymer-Interkalationsmittel ein Epoxid-Oligomer oder -Polymer darstellt, das durch Schmelzen des Epoxid-Oligomers oder -Polymers und Dispergieren des Phyllosilikats durch die gesamte Epoxid-Schmelze hindurch interkaliert wird.
34. Verfahren nach Anspruch 33, worin genanntes Dispergieren in einem Extruder erreicht wird.
35. Verfahren zur Herstellung der Nanocomposite-Zusammensetzung nach einem der Ansprüche 1 bis 6, umfassend das Interkalieren des Phyllosilikatmaterials mit einem Abstandsmittel aus quartären Oniumionen durch Kontaktieren des Phyllosilikats mit quartären Oniumionen in einem Molverhältnis von quartären Oniumionen : austauschbaren Kationen in der Phyllosilikat-Zwischenschicht von mindestens 0,25 : 1;
Bilden eines Gemischs aus dem interkalierten Phyllosilikatmaterial mit einem Anhydrid-Härtungsmittel und einem Anhydrid-härtbaren zweiten Interkalationsmittel aus Epoxidharz; und
Aussetzen des Gemischs gegenüber Bedingungen, die zur Reaktion und Polymerisation des Anhydrid-härtbaren Epoxidharzes mit einem Anhydrid-Härtungsmittel für das Epoxidharz zum Härten des Epoxidharzes, während es sich in Kontakt mit dem interkalierten Phyllosilikat befindet und zum miteinander Interkalieren des Epoxidharzes zwischen benachbarten Blättchen des Phyllosilikatmaterials, worin das Anhydrid-härtbare Epoxidharz in Mengen dergestalt kombiniert wird, dass das resultierende Verbundmaterial 40 % bis 99,95 % Epoxid-Oligomer oder -Polymer und 0,05 % bis 60 % interkaliertes Phyllosilikat enthält, ausreichend sind.
36. Verfahren nach Anspruch 35, worin das zweite Interkalationsmittel ein Anhydrid-härtbares Epoxidharz oder Monomer-Reaktanten, die zur Polymerisation zur Bildung eines Anhydrid-härtbaren Epoxidharzes fähig sind, darstellt.

Revendications

1. Composition nanocomposite comprenant de 0,05 pourcent en poids à 60 pourcent en poids d'un matériau de silicate stratifié intercalé avec un agent d'espacement des ions d'onium quaternaire ayant la structure :



dans laquelle X = N, P, O ou S et R₁, R₂, R₃ et R₄ sont les mêmes ou différents, et chacun représente un radical organique époxy non réactif ; et

de 40 pourcent en poids à 99,95 pourcent en poids d'un polymère de matrice comprenant une résine époxy traitée à l'anhydride qui n'est pas liée de manière covalente au matériau de silicate stratifié ou à l'agent d'espacement des ions d'onium, dans laquelle le matériau de silicate stratifié intercalé est dispersé uniformément dans le polymère de matrice.

2. Composition nanocomposite selon la revendication 1, dans laquelle les ions d'onium quaternaire comprennent au moins un fragment lié de manière covalente à un atome d'azote chargé positivement ayant une longueur d'au moins six atomes de carbone.
3. Composition nanocomposite selon la revendication 1 ou 2, formée en mettant en contact un phyllosilicate avec des ions d'onium quaternaire intercalants pour former une composition intercalante, ayant un rapport molaire ions d'onium quaternaire / cations échangeables de l'intercouche de phyllosilicate d'au moins 0,25 / 1 pour obtenir la sorption des ions d'onium quaternaire entre les couches espacées adjacentes du phyllosilicate pour agrandir l'espace entre une prédominance des lamelles de phyllosilicate adjacentes à au moins 3 Å, mesuré après la sorption des ions d'onium quaternaire, et un second agent intercalant placé entre les couches espacées adjacentes du matériau de phyllosilicate pour espacer le phyllosilicate adjacent d'au moins 3 Å supplémentaires, ledit second agent intercalant comprenant une résine époxy traitée à l'anhydride qui n'est pas liée de manière covalente au matériau de silicate stratifié ou à l'agent d'espacement des ions d'onium quaternaire, dans laquelle le matériau de silicate stratifié intercalé est uniformément dispersé dans le polymère de matrice.
4. Composition selon la revendication 3, dans laquelle le phyllosilicate intercalé est exfolié en une prédominance de lamelles individuelles.
5. Composition selon la revendication 3 ou 4, dans laquelle le rapport molaire ions d'onium quaternaire intercalants / cations échangeables de l'intercouche de phyllosilicate est au moins de 30 pourcent en mole, sur la base du nombre de moles des cations échangeables de l'intercouche dans le phyllosilicate.
6. Composition selon la revendication 5, dans laquelle le rapport molaire ions d'onium quaternaire intercalants / cations échangeables de l'intercouche de phyllosilicate est au moins de 50 pourcent en mole.
7. Composition de concentré nanocomposite comprenant de 10 % en poids à 90 % en poids d'un matériau de silicate stratifié intercalé avec un polymère ou un oligomère d'une résine époxy traitée à l'anhydride qui n'est pas liée de manière covalente au matériau de silicate stratifié, et de 10 pourcent en poids à 90 pourcent en poids d'un polymère de matrice comprenant une résine époxy traitée à l'anhydride, dans laquelle le matériau de silicate stratifié intercalé est dispersé uniformément dans le polymère de la matrice.
8. Composition nanocomposite selon la revendication 7, dans laquelle avant d'intercaler le matériau stratifié avec la résine époxy traitée à l'anhydride, le matériau de silicate stratifié est tout d'abord intercalé des ions d'onium quaternaire qui comprennent au moins un fragment lié de manière covalente à un atome d'azote comportant un proton ayant une longueur d'au moins six atomes de carbone.

9. Composition nanocomposite selon l'une quelconque des revendications précédentes, dans laquelle le polymère de matrice est co-intercalé dans le matériau de silicate stratifié.
- 5 10. Composition nanocomposite selon la revendication 9, dans laquelle le polymère de matrice est co-intercalé dans le matériau de silicate stratifié lorsqu'on disperse le matériau stratifié dans le polymère de matrice.
11. Composition nanocomposite selon la revendication 9, dans laquelle le polymère de matrice est co-intercalé dans le matériau de silicate stratifié avant qu'on disperse le matériau de silicate stratifié dans le polymère de matrice.
- 10 12. Procédé pour intercaler un phyllosilicate comprenant :

la mise en contact du phyllosilicate avec une composition intercalante comprenant un rapport molaire de 0,25 / 1 des cations d'ion d'onium quaternaire aux cations échangeables de l'intercouche de phyllosilicate, pour obtenir l'intercalation de, et l'échange ionique desdits cations d'ion d'onium quaternaire avec lesdits cations de l'intercouche, entre lesdites lamelles adjacentes de phyllosilicate en une quantité suffisante pour espacer lesdites lamelles adjacentes de phyllosilicate d'au moins 3 Å ; et

la co-intercalation du matériau de silicate stratifié intercalé avec les ions d'onium quaternaire avec une résine époxy pouvant être traitée à l'anhydride n'étant pas liée de manière covalente au matériau de silicate stratifié ou aux cations d'ions d'onium quaternaire, et un agent de traitement à l'anhydride de la résine époxy.
- 20 13. Procédé selon la revendication 12, dans lequel ladite composition intercalante comprend un transporteur d'eau comprenant de 5 % à 50 % en poids d'eau, sur la base du poids sec dudit phyllosilicate.
- 25 14. Procédé selon la revendication 12 ou 13, dans lequel la résine époxy pouvant être traitée à l'anhydride est co-intercalée dans le matériau de silicate stratifié en co-intercalant une résine époxy pouvant être traitée à l'anhydride, ou ses réactifs monomères capables de polymérisation pour former une résine époxy pouvant être traitée à l'anhydride.
- 30 15. Procédé selon la revendication 14, dans lequel l'agent intercalant de la résine époxy est compris dans une composition intercalante en une concentration de 10 à 100 % en poids, sur la base du poids sec du phyllosilicate.
- 35 16. Procédé de fabrication d'une composition selon l'une quelconque des revendications 1 à 11, dans lequel le phyllosilicate intercalé avec les ions d'onium quaternaire selon l'une quelconque des revendications 12 à 15 est co-intercalé avec un second agent intercalant sélectionné dans le groupe constitué d'un monomère polymérisable, un oligomère polymérisable, un polymère et un mélange de ceux-ci, ledit second agent intercalant étant un agent de traitement à l'anhydride et une résine époxy pouvant être traitée à l'anhydride ou des réactifs monomères capables de polymérisation pour former une résine époxy pouvant être traitée à l'anhydride, pour agrandir de manière supplémentaire l'espace entre une prédominance des lamelles de phyllosilicate adjacentes d'au moins 3 Å supplémentaires et disperser le matériau de silicate stratifié co-intercalé dans le polymère de matrice.
- 40 17. Procédé selon la revendication 16, dans lequel l'intercalaire est dispersé dans ledit polymère de matrice pour obtenir l'intercalation d'une partie du polymère de matrice entre les lamelles de phyllosilicate, en une quantité suffisante pour espacer lesdites lamelles de phyllosilicate adjacentes desdits au moins 3 Å supplémentaires.
- 45 18. Procédé selon la revendication 16 ou 17, dans lequel les ions d'onium quaternaire comprennent au moins un fragment lié de manière covalente à un atome d'azote ayant une longueur d'au moins six atomes de carbone.
- 50 19. Procédé selon l'une quelconque des revendications 12 à 18, comprenant en outre l'étape consistant à ajouter un accélérateur de traitement à la résine époxy pouvant être traitée à l'anhydride pour l'intercalation d'une partie de l'accélérateur de traitement dans le phyllosilicate ainsi que dans la résine époxy pouvant être traitée à l'anhydride.
- 55 20. Procédé selon l'une quelconque des revendications 12 à 19, dans lequel le polymère de matrice est une résine époxy pouvant être traitée à l'anhydride et comprenant en outre l'étape consistant à ajouter un agent de traitement à l'anhydride au polymère de matrice avant de disperser ledit phyllosilicate intercalé avec les ions d'onium quaternaire dans le polymère de matrice.
21. Procédé selon l'une quelconque des revendications 12 à 20, comprenant en outre l'étape consistant à mélanger le phyllosilicate intercalé avec les ions d'onium quaternaire avec la résine époxy pouvant être traitée à l'anhydride,

puis à ajouter l'agent de traitement à l'anhydride au mélange.

22. Procédé selon la revendication 21, comprenant en outre l'étape consistant à ajouter un accélérateur de traitement au mélange de phyllosilicate intercalé avec les ions d'onium quaternaire et de résine époxy.
23. Procédé selon l'une quelconque des revendications 12 à 22, comprenant en outre l'étape consistant à ajouter un agent de traitement à l'anhydride au phyllosilicate intercalé avec les ions d'onium quaternaire avant de disperser l'intercalaire dans la résine époxy pouvant être traitée à l'anhydride.
24. Procédé selon la revendication 23, comprenant en outre l'étape consistant à ajouter un accélérateur de traitement au phyllosilicate intercalé avec les ions d'onium quaternaire avant de disperser l'intercalaire dans la résine époxy pouvant être traitée à l'anhydride.
25. Procédé selon l'une quelconque des revendications 16 à 24, dans lequel ledit phyllosilicate est mis en contact avec lesdits ions d'onium quaternaire intercalants, et une résine époxy pouvant être traitée à l'anhydride, dans lequel la concentration des ions d'onium quaternaire est dans un rapport molaire ions d'onium quaternaire / cations échangeables de l'intercouche de phyllosilicate d'au moins 0,25 / 1.
26. Procédé selon la revendication 25, dans lequel ledit phyllosilicate est mis en contact avec les ions d'onium quaternaire intercalants et une résine époxy pouvant être traitée à l'anhydride, dans lequel la concentration des ions d'onium quaternaire est dans un rapport molaire ions d'onium quaternaire / cations échangeables de l'intercouche de phyllosilicate d'au moins 0,5 / 1.
27. Procédé selon la revendication 26, dans lequel ledit phyllosilicate est mis en contact avec lesdits ions d'onium quaternaire intercalants et une résine époxy pouvant être traitée à l'anhydride et un agent de traitement à l'anhydride dans lequel la concentration des ions d'onium quaternaire est dans un rapport molaire ions d'onium quaternaire / cations échangeables de l'intercouche de phyllosilicate d'au moins 1 / 1.
28. Procédé selon l'une quelconque des revendications 16 à 27, dans lequel le rapport molaire ions d'onium quaternaire / cations de l'intercouche de phyllosilicate est d'au moins 0,25 / 1 ;
combinant le phyllosilicate intercalé avec une composition intercalante comprenant un polymère thermoplastique ou thermodurcissable, et chauffant le polymère thermoplastique suffisamment pour fournir l'écoulement dudit polymère thermoplastique ; et
dispersant ledit phyllosilicate intercalé dans un polymère de matrice époxy pouvant être traité à l'anhydride.
29. Procédé selon la revendication 28, dans lequel la composition intercalante comprend de 10 % à 200 % en poids dudit intercalant de résine époxy pouvant être traitée à l'anhydride, sur la base du poids sec de phyllosilicate avec lequel la composition intercalante entre en contact.
30. Procédé selon la revendication 28 ou 29, dans lequel la quantité d'agent d'espacement / de couplage des ions d'onium quaternaire intercalants dans le matériau de phyllosilicate est dans un rapport molaire d'au moins 1 / 1, ions d'onium quaternaire / cations échangeables dans les espaces de l'intercouche du matériau de phyllosilicate.
31. Procédé selon la revendication 30, dans lequel le rapport molaire de l'agent d'espacement / de couplage des ions d'onium quaternaire intercalés aux cations de l'intercouche de phyllosilicate est de 1 / 1 à 1 / 5.
32. Procédé selon l'une quelconque des revendications 28 à 31, dans lequel le rapport en poids de l'intercalant en polymère thermoplastique ou thermodurcissable au matériau de phyllosilicate, sur la base de la matière sèche, est de 20 grammes d'intercalant époxy par 100 grammes de matériau de phyllosilicate à 200 grammes d'intercalant époxy par 100 grammes de matériau de phyllosilicate.
33. Procédé selon l'une quelconque des revendications 28 à 32, dans lequel l'intercalant de polymère est dans un oligomère ou polymère époxy intercalé dans le phyllosilicate en coulant l'oligomère ou polymère époxy et en dispersant le phyllosilicate dans la coulée époxy.
34. Procédé selon la revendication 33, dans lequel ladite dispersion est accomplie dans une extrudeuse.
35. Procédé de fabrication de la composition nanocomposite selon l'une quelconque des revendications 1 à 6, com-

prenant l'intercalation du matériau de phyllosilicate avec un agent d'espacement des ions d'onium quaternaire en mettant en contact le phyllosilicate avec les ions d'onium quaternaire dans un rapport molaire ions d'onium quaternaire / cations échangeables de l'intercouche de phyllosilicate d'au moins 0,25 / 1 ;

la formation d'un mélange du matériau de phyllosilicate intercalé avec un agent de traitement à l'anhydride et un second agent intercalant de résine époxy pouvant être traité à l'anhydride ; et

la soumission du mélange à des conditions suffisantes pour réagir et polymériser la résine époxy pouvant être traitée à l'anhydride avec un agent de traitement à l'anhydride pour la résine époxy pour traiter la résine époxy lorsqu'elle est en contact avec le phyllosilicate intercalé et pour co-intercaler la résine époxy entre les lamelles adjacentes du matériau de phyllosilicate, dans lequel la résine époxy pouvant être traitée à l'anhydride est combinée en des quantités telles que le matériau composite résultant contient de 40 % à 99,95 % d'oligomère ou de polymère époxy et de 0,05 % à 60 % de phyllosilicate intercalé.

36. Procédé selon la revendication 35, dans lequel le second agent intercalant est une résine époxy pouvant être traitée à l'anhydride, ou des réactifs monomères capables de polymérisation pour former une résine époxy pouvant être traitée à l'anhydride.




Fig. 1




Fig. 2